



# Product Data Sheet

## Rubber Powder Ecorr<sup>®</sup> RNM60

### Chemical Properties

Acetone-extract, %	ASTM D297-18	<	13
Ashes, %	ASTM D297-18	<	11
Carbon black, %	ASTM E1131	29 ±	2
Polymer content, %	ASTM E1131	54 ±	4

### Sieve Analysis, % Retained

50 Mesch = 0.300 mm	ASTM D5644	<	16
60 Mesch = 0.250 mm	ASTM D5644	<	45
100 Mesch = 0.150 mm	ASTM D5644	<	75
140 Mesch = 0.106 mm	ASTM D5644	<	90
200 Mesch = 0.075 mm	ASTM D5644	<	98

**Packaging:** Big-bags 1000 kg or 20 kg PE bags

**Appearance:** Black powder

**Produced by:** Rubber Resources, Maastricht

Issued: 17-07-2001 The values in this Product Data Sheet are given as an indication without implying and undertaking on our part.

**Rubber Resources B.V.**

[www.rubber-resources.com](http://www.rubber-resources.com)

Lage Frontweg 2A - 6219 PD Maastricht - The Netherlands - P.O. Box 437 - 6200 AK Maastricht - The Netherlands

Phone: +31 (0)43 - 329 04 44 - Fax: +31 (0)43 - 325 71 91 - E-Mail: [info@rubber-resources.com](mailto:info@rubber-resources.com)

*Our General Conditions of Sale are an indissoluble part of our offers and agreements we will conclude or we have concluded with you. We explicitly reject General Conditions of others. Our Conditions of Sale have been filed with the Chamber of Commerce in Maastricht and can be obtained from us free of charge. Dutch Trade Register, no. 14633389.*